

Test Report

No. E100317021C-01

SHENZHEN ART-TECH R/C HOBBY CO.,LTD
3/F,NO.1 D4 LIYUAN INDUSTRIAL AREA, LANG XIN COMMUNITY, SHIYAN STR, BAOAN DISTRICT, SHENZHEN
CITY CHINA

Report on the submitted sample said to be V22 Osprey
M/N : Art-tech standard version 4ch (Btypy 2.4G Tx)
Item No./Lot No. : 11011118101
Sample Received Date : Mar.17.2010
Testing Completed Date : Apr.03.2010

Test Requested : For compliance with RoHS directive 2002/95/EC and its amended directives


Test Method : 1. Review was performed for the samples disjointed from the submitted articles and the related test reports submitted by the Applicant.
2. Tests was performed for the samples indicated by the photos in the report with test methods according to IEC 62321:2008 Ed.1: Procedures for the Determination of Levels of Six Regulated substances in Electrotechnical Products.
(1) Screening by XRF Spectroscopy.
(2) Wet Chemical Test
a. Determination of Lead & Cadmium & Mercury by ICP & AAS.
b. Determination of Hexavalent Chromium by UV-VIS.
c. Determination of PBBs and PBDEs by GC/MS.

Test Results : Please refer to next page.

Signed for and on behalf of
Dong Guan EMTEK Co., Ltd .

Apr.03.2010

Manager



No. E100317021C-01

Test Results:

No.	Name of the Sample	Part name	Sample Description	Pb (ppm)	Cd (ppm)	Hg (ppm)	Cr (ppm)	Br (ppm)	
1-1	Shell	Body of plane	Plastic w/blue/black printing	BL	BL	BL	BL	BL	
1-2		Window	Transparent plastic	BL	BL	BL	BL	BL	
1-3		Empennage	Plastic w/blue/black printing	BL	BL	BL	BL	BL	
1-4-1		Front wings	Plastic w/blue/black printing	BL	BL	BL	BL	BL	
1-4-2			White foam	BL	BL	BL	BL	BL	
1-5-1		Wheel	Black plastic	BL	BL	BL	BL	BL	
1-5-2			Silver metal	BL	BL	BL	BL	N.A.	
2-1-1		Propeller	Bracket	Silver metal	BL	BL	BL	BL	N.A.
2-1-2	Black plastic			BL	BL	BL	BL	BL	
2-2	Stabilizer bar		Black plastic	BL	BL	BL	BL	BL	
2-3	Balance beam		Silver metal	BL	BL	BL	BL	N.A.	
2-4	Propeller chip		Black plastic	BL	BL	BL	BL	BL	
2-5	Fixed rack		Black plastic	BL	BL	BL	BL	BL	
2-6	Axle		Silver metal	BL	BL	BL	IN	N.A.	
2-7-1	Pillar		Silver metal	BL	BL	BL	BL	N.A.	
2-7-2			Black plastic	BL	BL	BL	BL	BL	
2-8-1	Gear		White	BL	BL	BL	BL	BL	
2-8-2			Copper metal	IN	BL	BL	BL	N.A.	
2-9	Motor seat		Black plastic	BL	BL	BL	BL	BL	
3	Accessories		Screw	Silver metal	BL	BL	BL	BL	N.A.

Note : ppm = mg/kg=parts per million N.A.=Not Applicable BL= Below Limit
IN= Inconclusive,chemical analysis necessary
Testing results are only used for reference.

No. E100317021C-01

Test Results:

Test Item	Result(ppm)	Detection Limit	Law Limit
	2-8-2*		
Lead (Pb)	24716	2 ppm	1000 ppm

Test Item	Result(ppm)	Detection Limit	Law Limit
	2-6		
Hexavalent Chromium (Cr ⁶⁺)	Negative	See Note 1	#

- Note : 1. Negative = absence of Cr(VI) in the metallic sample
 Positive = presence of Cr(VI) in the metallic sample
 (The tested sample should further verified by boiling-water-extraction method if the spot test result cannot be confirmed or spot test result is negative)
 Boiling-water-extraction :
 Negative = absence of Cr(VI) in the metallic sample
 Positive = presence of Cr(VI) in the metallic sample
 Boiling-water-extraction solution is equal or greater that 0.02mg/kg with 50cm² sample surface area
2. # = Positive indicates the presence of Cr(VI) on the tested areas
 Negative indicates the absence of Cr(VI) on the tested areas
- * Lead in glass, ceramic of electronic components which are exempted from (RoHS) the requirements.
 Lead as an alloying element in steel containing up to 0.35% lead by weight, aluminum containing to 0.4% lead by weight and as a copper alloy containing up to 4% lead by weight. which are exempted from (RoHS) the requirements.

No. E100317021C-01

Remark :

- (1) (a) It is the result on total Br while test item on restricted substances is PBBs/PBDEs. It is the result on total Cr while test item on restricted substances is Cr⁶⁺.
- (b) Results are obtained by EDXRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-VIS (for CrVI) and GC-MS (for PBBs, PBDEs) is recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321:2008 Ed.1 (unit: mg/kg)

Element	Polymer	Metal	Composite Materials
Cd	$BL \leq (70-3\sigma) < X < (130+3\sigma) \leq OL$	$BL \leq (70-3\sigma) < X < (130+3\sigma) \leq OL$	$LOD < X < (150+3\sigma) \leq OL$
Pb	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma) \leq OL$
Hg	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (700-3\sigma) < X < (1300+3\sigma) \leq OL$	$BL \leq (500-3\sigma) < X < (1500+3\sigma) \leq OL$
Br	$BL \leq (300-3\sigma) < X$	---	$BL \leq (250-3\sigma) < X$
Cr	$BL \leq (700-3\sigma) < X$	$BL \leq (700-3\sigma) < X$	$BL \leq (500-3\sigma) < X$

(c) OL = Over Limit, BL = Below Limit, LOD = Limit of Detection, --- = not conducted.

(d) The XRF screening test for RoHS elements – The reading may be different to the actual content in the sample be of non-uniformity composition

- (2) (a) mg/kg = ppm=0.0001%, N.D. = not detected,
(b) Unit and Detection Limit in wet chemical test

Test Items	Pb	Cd	Hg
Units	mg/kg	mg/kg	mg/kg
Detection Limit	2	2	2

The Detection Limit for single compound of PBBs & PBDEs is 5 mg/kg and Detection Limit of Cr⁶⁺ for polymer & composite sample is 2 mg/kg.

- (c) According to IEC 62321:2008 Ed.1, result on Cr⁶⁺ for metal sample is shown as Positive/Negative.
Negative = Absence of Cr⁶⁺ coating, Positive = Presence of Cr⁶⁺ coating

No. E100317021C-01

Photo Appendix

